

Product Information: ZOUCH 2000 Sealer - Highly Compressive Special E.P.D.M. Foam

Application Light duty water tightness, medium duty air tightness, sound absorption, heat insulation and cushioning

Product Properties - Not for specification purposes	
Specifications	N/A
Sound Absorption	(500-2000 Hz) - Excellent
Temperature Range	-40°C to 135°C
High Intermittent	180°C
Water Absorption	3.1% (50% Compression)
Tensile Strength	9cm ²
Flammability	FMVSS 302
Cellular Structure	Special Semi-Closed Cell
Density	95 kg/m ³
25% Compression Deflection	0.2cm ²
Air Permeability	Very Low
Weatherability	Excellent
Thermal Conductivity	0.037 Kcal/m/h/°C
Adhesive Strength	Stainless (20°C) - N/15MM - 8.6
Colour	Black

Processing Supplied Die-cut Shapes, Coils, Sheets and Rolls

Storage Unprocessed in the original cardboard box, 6 months after receipt by the customer, at a relative atmospheric humidity of about 60% and a temperature of 18°C.

Special Information

All data and technical information are based on laboratory tests or have been compiled from supplier information to the best of our knowledge. A guarantee that the values are complete and correct can however not be given. You are kindly requested to conduct your own tests to determine the suitability of our product for your applications. Our General Conditions answer any questions on guarantees and liabilities for these products insofar as no other legal regulations apply.

09/2008