

## ZOUCHmount Sekure

Double Sided PVC Foam Tape -Security glazing tape independently tested to BS 7950

|                                     |                       |                 |
|-------------------------------------|-----------------------|-----------------|
| Adhesive type                       | Acrylic               |                 |
| Adhesive coat weight (total)        | 75                    | gsm             |
| Liner type                          | Glassine paper, Amber |                 |
| Foam density                        | 200                   | Kg per cu metre |
| Shore Hardness (00 Scale)           | 40                    |                 |
| Force to compress to 25%            | 0.63                  | Kg per squ cm   |
| Tensile strength MD                 | 550                   | kPa             |
| Elongation at break MD              | 160                   | %               |
| Liner release                       | 10 max.               | N/m             |
| Service temperature                 | -20 to +90            | Deg. C          |
| UV resistance                       | Excellent             |                 |
| Fungi resistance                    | Excellent             |                 |
| Oxidation resistance                | Excellent             |                 |
| Weather resistance                  | Excellent             |                 |
| Recommended application temperature | +10 to +40            | Deg. C          |
| Shelf life                          | 12                    | Months          |

**Processing** The most important processing parameters and information on cleaning are listed in our Information on Processing Adhesive Tapes.

**Storage** Unprocessed in the original cardboard box, 12 months after receipt by the customer, at a relative atmospheric humidity of about 60% and a temperature of 18°C.

### Special Information

All data and technical information presented are based on laboratory tests or have been compiled from supplier information to the best of our knowledge. A guarantee that the values are complete and correct can however not be given. You are kindly requested to conduct your own tests to determine the suitability of our product for your applications. Our General Conditions answer any questions on guarantees and liabilities for these products insofar as no other legal regulations apply.

03/2007